

Vision Blackback Stretch Elite



dpm
digital print media

Technical Data Sheet

Vision Blackback Stretch Elite

Knitted polyester with a black block-out rear face suitable printing UV and direct sublimation using diverse inks. Finished with FR treatment.

Material 100 % Polyester
with additional, onesided block-out coating

Stock widths app. 320 cm

Finishing Rolled on paper cores

Weight

acc. to DIN EN 12127	235.00	[g/m ²]	+ - 3	[%]
----------------------	--------	---------------------	-------	-----

Shrinkage

Heat Shrinkage, 195 °C, 90 sec,
lengthwise

acc. to AA 25-02	-5.00	[%]	+ - 1	[%]
------------------	-------	-----	-------	-----

Heat Shrinkage, 195 °C, 90 sec,
crosswise

acc. to AA 25-02	-1.00	[%]	+ - 1	[%]
------------------	-------	-----	-------	-----

Tearing strength

Elongation at 100 N, longitudinal direction

acc. to DIN EN ISO 13934-1	18.00	[%]	+ - 10	[%]
----------------------------	-------	-----	--------	-----

Elongation at 100 N, cross direction

acc. to DIN EN ISO 13934-1	22.00	[%]	+ - 10	[%]
----------------------------	-------	-----	--------	-----

Maximum tensile elongation, longitudinal
direction

acc. to DIN EN ISO 13934-1	50.00	[%]	+ - 20	[%]
----------------------------	-------	-----	--------	-----

Maximum tensile elongation, cross direction

acc. to DIN EN ISO 13934-1	75.00	[%]	+ - 20	[%]
----------------------------	-------	-----	--------	-----

Maximum tearing strength, longitudinal
direction

acc. to DIN EN ISO 13934-1	min. 250.00	[N/5 cm]
----------------------------	-------------	----------

Maximum tearing strength, cross direction

acc. to DIN EN ISO 13934-1	min. 620.00	[N/5 cm]
----------------------------	-------------	----------



Digital Print Media, The Heights, Ibstone Road, Stokenchurch, Bucks, HP14 3BG
T : 01494 760 240 E : sales@dpm.com W : www.dpm.com